

Certificate


Certificate of Analysis

Reference Material 2202-SA Secondary Alumina

Analyte	Certified value	Uncertainty
Mass fraction in %		
Na ₂ O	0,78	± 0,26
SiO ₂	0,018	± 0,008
Fe ₂ O ₃	0,036	± 0,005
ZnO	0,0031	± 0,0012
CaO	0,040	± 0,005
TiO ₂	0,0029	± 0,0007
P ₂ O ₅	< 0,005	

Analyte	Certified value	Uncertainty
Mass fraction in %		
MnO	< 0,002	
V ₂ O ₅	< 0,005	
Ga ₂ O ₃	0,012	± 0,004
C	0,22	± 0,08
S	< 0,5	
F	2,6	± 1,0
α-Al ₂ O ₃	4,8	± 1,4

Date of issue: August 31, 2022



Reference material 2202-SA

Description

The base material for this secondary Alumina reference material has been taken directly from the production cycle after gas treatment process of an Aluminum smelter. This is process material which can be regarded as sufficiently homogeneous.

Grainsize D90: $130 \pm 19 \mu\text{m}$

This reference material was certified in an interlaboratory test of 7 laboratories. The values given in this certificate are taken from the evaluation of the interlaboratory test.

The uncertainties were estimated at a 95 % confidence level, showing both the contribution of homogeneity and the uncertainties of the analytical methods used. The uncertainty values were calculated from the reproducibility standard deviations of the ILT with a coverage factor $k = 2$.

The certified values are given as oxides on an equivalent weight basis and assume stoichiometry in the oxide form listed.

Recommended use

This reference material is intended for the verification of analytical methods such as XRF, XRD, ICP OES or calibration of analytical instruments.

Storage information

This reference material should be stored in a dry and clean environment at room temperature, e.g. storage in desiccator.

Methods used for characterization

XRF, XRD and combustion analysis.

Disclaimer

We inspect and test to the best of our knowledge and belief and assume no further liability for the accuracy of the inspection and test.

Contact

For more information see www.metallogie.de/ringversuche/

META<L>LOGIE, c/o pdv-software GmbH
Im Schleeke 50, 38642 Goslar, Germany

E-Mail: ringversuch@metallogie.de